



ZINC SPRAY

ET885003-LG, light grey 400ml

	Product	Anticorrosive cold galvanizing spray based on monocomponent zinc with high molecular weight. Professional quality result. Quick drying.
	Surface Preparation	Clean and degrease.
†	Application Conditions	12-30°C Shake well before application.
	Number of Layers	2 coats at 10-15cm distance.
/ _↑ / _↑ /	Flash off	5-10min
	Drying	Dust free at 3-5min at 20°C. In depth drying 8-12 hours.
	Cleaning of equipment	After the application turn the can upside down and press the nozzle for 5sec.
	Shelf life	5 years

Technical Data Sheet etalon-refinish.com